

STUDY ON BUCKLING EFFECT OF CUTOUTS ON THE OPTIMIZED FIBRE ORIENTATED LAMINATED COMPOSITE PLATE

Anu George¹, S. Usha²

¹ M. Tech Scholar, Civil Department, SNG College of Engineering, Kerala, India

² Professor, Civil Department, SNG College of Engineering, Kerala, India

¹anugeorge023@gmail.com, 09539258170

Abstract- Laminate composite materials are composite materials in which layers of different properties are bonded together to act as an integral part. In structures, cutouts provided in laminated composite plate show reduction in strength, stiffness and inertia. Laminated composite plates have wide application in the aerospace, automotive, marine and civil areas. Cutouts are necessary to serve the purpose of weight reduction, venting and attachments to other units for the cable to pass through are so on. This paper compares the critical buckling load of the laminated composite plate with and without cutout by changing the fibre orientation by experimental and numerical methods. Glass/epoxy laminated composite plate was used here. Laminated composite plate with circular cutout shows a decrease in buckling load than plates without cutout. Also the buckling load decreases with increase in fibre angles. The maximum buckling load combination was obtained with fibre orientation 45/-45/45/-45/45/-45/45/-45 with circular cutout.

Key Words- Buckling Analysis, Circular, Cutouts, Finite Element Method, Glass Fibre, Hardener, Laminated Composite Plate, Resin

1. INTRODUCTION

A lamina is fibre reinforced composite, prepared from fibres and matrix (sometimes woven fabric may also used for making lamina). Laminae having varying fibre orientations are bonded together to form an integral structural component, which is known as laminate. A lamina is considered to be homogenous at macroscopic level. It has three planes of symmetry and hence termed as orthotropic. The laminates may be symmetric or anti-symmetric or unsymmetric. The mechanical performance of laminated composite plates are highly dependent on the degree of orthotropy of individual layers, the low ratio of transverse shear modulus to in-plane modulus and the stacking sequence of laminates. Lamination is used to bond the best aspects of the adjoining layers and bonding material to develop a more useful material.




Fig -1: Laminated Composite Plate

Glass-reinforced plastic is a composite material made of epoxy resin matrix reinforced by fine fibers made of E glass. GRP is a lightweight, strong material with very many uses, including boats, automobiles, water tanks, roofing, pipes and cladding. Moreover, by placing multiple fiber layers on top of other, with each fiber layer oriented (stacked) in different preferred directions, the strength and stiffness parameters of the entire material can be enhanced in an efficient manner.

The mechanical behaviour of laminated composite plates are strongly dependent on the degree of orthotropy of individual layers, the low ratio of transverse modulus of rigidity to the in-plane modulus of elasticity and the stacking sequence of laminates. Lamination helps to combine the better aspects of the combining layers and bonding material in order to achieve a useful composite material. Fiber-reinforced composites are extensively used in the form of relatively thin plate, and they have consequently higher load carrying capability against buckling.

2. SCOPE

Laminated composite plates have wide application in the aerospace, automotive, marine and civil areas. In structures, laminated composite plate consists of cutout which reduces their strength, stiffness and inertia. Cutouts are necessary to serve the purpose of weight reduction, inspection, venting and attachment to other units for the cable to pass through are so on. Cutouts are required for ventilation as well. Hence the effects of cutout in laminated composite plate are to be investigated.

3. OBJECTIVES

- To determine the critical buckling load of laminated composite plate without cutout and with circular cutout by changing the fibre orientation by experimental and numerical methods.
- To optimize the fibre orientation by performing the buckling analysis using numerical methods.

4. EXPERIMENTAL PROGRAM

4.1 MATERIALS

The materials used for making the laminated composite plate are:

4.1.1 Glass Fibre

The bidirectional glass fibre woven roving of 360 GSM with 0.3 mm thickness was used for the experimental work.

4.1.2 Epoxy Resin

Araldite LY 556 was used as epoxy resin which is medium viscosity, unmodified liquid epoxy resin based on Bisphenol-A.

4.1.3 Hardener

Low viscosity, unmodified, aliphatic polyamine hardener, Aradur HY 951 was used for the experiment which has excellent water resistance property.

4.1.4 Polyvinyl Alcohol

Polyvinyl Alcohol act as a releasing agent applied by means of spray gun.

4.2. MIXING RATIO

Araldite LY 556 and Aradur 951 were mixed well before applying into laminated composite plate. Resin and hardener should be mixed uniformly until a homogenous mixture is formed. It provides a low viscosity, solvent free room temperature curing laminating system. By varying the contents of hardener from 10 to 12 parts, the reactivity of the system can be adapted to suit the processing and curing conditions.

Table -1: Properties of the Mix

| | | |
|-----------------------|----------------------|-----------------|
| Viscosity | at 25 ⁰ C | 1700 mPa.s |
| | at 40 ⁰ C | 650 mPa.s |
| Useable Life Gel Time | upto 1500 mPa.s | 10 minutes |
| | at 25 ⁰ C | 120-180 minutes |
| | at 40 ⁰ C | 30 minutes |

4.3 PREPARATION OF LAMINATED COMPOSITE SPECIMEN

The laminated composite plate specimens used in this research were made from 0/90 woven glass fiber with epoxy matrix. Hand layup technique was used for fabrication of plates. The percentage of glass fiber and mixture of epoxy resin and hardener had taken as 1:1 in weight for fabrication of the plates. A rigid platform made of iron was selected to make a flat surface. A milosh sheet was placed on the rigid platform. Then polyvinyl alcohol i.e releasing agent was applied on the milosh sheet by using the sprayer. After applying that, gel coat (mixture of epoxy resin and hardener) was spread to provide a smooth surface and to avoid the direct exposure of the fibre to environment. Glass fibres from the rovings were placed on the top of the gel coat and again gel coat was applied. The entrapped air was removed by using the steel rollers. The process was continued as above before the gel coat had fully hardened. After the completion of all layers, again a milosh sheet was placed on the top of the gel coat by applying poly vinyl alcohol. A heavy metal rigid platform was placed over it. Then the whole mould was kept at the compression moulding machine for 20 minutes. The temperature was kept at 80°C. After 20 minutes, switch off the machine and kept the specimen for 4 hours. After 48 hours of curing, cut the specimen in the desired size by water jet cutting with and without cutout for the experimental study.



Fig -2: Pouring of Epoxy Resin



Fig -3: Removal of Entrapped Air by Rollers



Fig -4: Temperature Setting in Machine



Fig -5: Prepared Plate without Cutout



Fig -6: Prepared Plate with Cutout

A total of seven types of laminated composite plate with and without circular cutout of different fibre orientation were prepared for the experimental study.

1. Laminated composite plate 0/90/0/90/0/90/0/90 orientation without cutout (LCPWOC 1)
2. Laminated composite plate 45/-45/45/-45/45/-45/45/-45 orientation without cutout (LCPWOC 2)
3. Laminated composite plate 0/90/0/90/0/90/0/90 orientation with cutout (LCPWC 1)
4. Laminated composite plate 45/-45/45/-45/45/-45/45/-45 orientation with cutout (LCPWC 2)
5. Laminated composite plate 0/90/45/-45/45/-45/0/90 orientation with cutout (LCPWC 3)
6. Laminated composite plate 0/90/60/30/60/30/0/90 orientation with cutout (LCPWC 4)
7. Laminated composite plate 60/30/60/30/0/90/0/90 orientation with cutout (LCPWC 5)

4.4 TEST PROCEDURE

The specimens were tested in an axial compression testing machine having a capacity of 100 kN. The specimen was placed vertically and clamped at top and bottom ends. The other two ends were kept as free. All specimens were loaded slowly until buckling. For axial loading, the plate specimen was placed between the two machine heads, of which the lower head was permanently fixed and the upper head was moving during the test with the help of hydraulic cylinder. The plate was loaded at the rate of 2 mm/min. As the load starts increasing, the dial gauge needle also moves and at a particular point, there was a sudden movement of the needle. The load at this point was the buckling load of the specimen. The testing machine was connected to the computer to obtain the load displacement curve and the critical buckling load. The initial part of the curve was linear, the point where the curve deviates from its linearity was taken as the critical buckling load.

4.5 EXPERIMENTAL RESULTS

The buckling load and load versus displacement curve of the maximum buckling load with circular cutout specimen obtained from the experiment is shown in figure 7.




Fig -7: Load Displacement Curve of LCPWC 2

5. FINITE ELEMENT ANALYSIS

Finite element analysis of the above seven different plates were done using the software ‘ANSYS 14.5 APDL’ also.

Table -2: Element Type and Material Properties

| Material No: | Element Type | Material Property |
|--------------|--------------|---------------------------------|
| 1 | Shell 281 | Density = 1.2 g/cm ³ |
| | | Youngs modulus E = 10 GPa |
| | | Poissons ratio = 0.12 |

‘Shell 281’ element was used to model the laminated composite plate. This is an eight- node linear shell element having six degrees of freedom at each node. Those are translation in x, y, z direction and rotation about x, y, z axis. It was used in cases for linear, large rotation, and/or large strain nonlinear applications.




Fig -8: Boundary Condition of Plate with Circular Cutout

5.1 FINITE ELEMENT RESULTS

The plate specimens were modelled in ANSYS software. Analysis of plates was done to obtain critical buckling load.

Table -3: Results obtained from ANSYS 14.5

| ID No. of Plate Specimen | Buckling Load (kN) |
|--------------------------|--------------------|
| LCPWOC 1 | 5.8 |
| LCPWOC 2 | 6.1 |
| LCPWC 1 | 4.9 |
| LCPWC 2 | 4.8 |
| LCPWC 3 | 4.68 |
| LCPWC 4 | 4.482 |
| LCPWC 5 | 4.68 |

6. RESULTS AND DISCUSSION

Results obtained from software were compared with the experimental results for the seven laminated plate specimens. The results showed satisfactory convergence.

Table -4: Comparison between Experimental Value and Software Value

| ID No. of Plates | Buckling Load | | Percentage Variation |
|------------------|--------------------|----------------|----------------------|
| | Experimental Value | Software Value | |
| LCPWOC 1 | 6.4 | 5.8 | 9.375 |
| LCPWOC 2 | 6.6 | 6.1 | 9.09 |
| LCPWC 1 | 4.78 | 4.9 | 2.44 |
| LCPWC 2 | 4.9 | 4.8 | 2.04 |
| LCPWC 3 | 4.62 | 4.68 | 1.28 |
| LCPWC 4 | 4.7 | 4.482 | 4.63 |
| LCPWC 5 | 4.7 | 4.68 | 1.5 |




Chart -1: Comparison of Buckling Load

The maximum buckling load capacities was obtained with LCPWC 2 (fibre orientation 45/-45/45/-45/45/-45/45/-45 with circular cutout). The percentage reduction due to the circular cutout at centre was 25 % compared to laminate without cutout.

7. ACKNOWLEDGEMENT

The authors would like to thank the Composite Technology Centre, Aerospace Engineering Department, IIT Madras for giving them the opportunity to conduct and complete the experimental work.

8. CONCLUSIONS

Experimental results on laminated composite plate of size 250 mm x 250 mm x 1.6 mm with different seven cases were compared with results obtained in the buckling analysis in ANSYS 14.5 software. The results are summarized as below:

- Laminated plates with cutout shows a decrease in buckling load carrying capacity compared to plate without cutout.
- The maximum buckling load depends on fibre orientation of the different layers used. It is observed that the laminated composite plate with fibre orientation 45/-45/45/-45/45/-45/45/-45 shows the maximum buckling load.
- The percentage reduction in buckling load carrying capacity was observed as 25% for LCPWC 2 compared with LCPWOC.

REFERENCES:

1. M Mohan Kumar, Colins V Jacob , Lakshminarayana N , Puneeth BM , M Nagabhushana, "Buckling Analysis of Woven Glass Epoxy Laminated Composite Plate", American Journal of Engineering Research (AJER), e-ISSN : 2320-0847 p-ISSN: 2320-0936 Volume-02, Issue-07, pp-33-40, 2013
2. Pandey M D, "Effect of Fiber Waviness on Buckling Strength of Composite Plate", Journal of Engineering Mechanics, (1999), pp. 1173-1179
3. K.Vasantha Kumar , Dr.P.Ram Reddy , Dr.D.V.Ravi Shankar, "Effect of Angle Ply Orientation On Tensile Properties Of Bi Directional Woven Fabric Glass Epoxy Composite Laminate", International Journal of Computational Engineering, Issn 2250-3005, Researc, Vol, 03, Issue, 10, October, 2013
4. Shukla K.K, Kreuzer E, Sateesh Kumar K.V, Nath Y, "Buckling of Laminated Composite Rectangular Plate, Journal of Aerospace Engineering", pp. 215-223, October 2005
5. Sandeep M.B , D.Choudhary , Md. Nizamuddin Inamdar , Md. Qalequr Rahaman, "Experimental Study Of Effect of Fiber Orientation on the Flexural Strength of Glass/Epoxy Composite material", International Journal of Research in Engineering and Technology eISSN: 2319-1163, p ISSN: 2321-7308, Volume: 03 Issue: 09, September, 2014

6. Liecheng Sun, Issam E Harik, "Buckling of Stiffened Antisymmetric Laminated Plates", Journal of Engineering Mechanis(ASCE), pp.1110-1123, August, 2013
7. Adnan Naji Jameel, Dr. Louay Sabah Yousaf, "Buckling Analysis of Stiffened and Unstiffened Laminated Composite Plates", Journal of Engineering, (August 2014)No.8, Vol.20
8. Basharia A.A. Yousef, Mohamed H. Elsheikh, Mohd F. M. Sabri, Hakim S. S. Aljibori, Suhana M. Said, "Effect of Buckling on Glass Fiber/Epoxy Plate", International Journal of Engineering Research and Development e-ISSN: 2278-067X, p-ISSN : 2278-800X, Volume 5, Issue 5, PP. 60-68, December, 2012
9. Nagendra Singh Gaira, Nagengra Kumar Maurya, Rakesh Kumar Yadav, "Linear Buckling Analysis of Laminated Composite Plate, International Journal of Engineering Science and Technology", ISSN: 2250-3676 Vol. 2, Issue 4, pp. 886-891, July-August, 2014
10. K.Mallikarjuna Reddy, B.Sidda Reddy, R.Madhu Kumar, "Buckling Anlysis of Laminated Composite Plates Using Finite Element Method ", International Journal of Engineering Sciences and Research Technology, ISSN: 2277-9655, 3281-3286, November, 2013
11. Zhang Y.X. and Yang C.H., "Recent developments in finite element analysis for laminated composite plates", (2009), Composite Structures 88, Science Direct, pp. 147-157
12. Amit Kumar Tanwer, "Mechanical Properties Testing of Uni-directional and Bi-directional Glass Fibre Reinforced Epoxy Based Composites", International Journal of Research in Advent Technology, Vol.2, No.11, E-ISSN: 2321-9637, November 2014
13. Sidda Reddy B, "Vibration Analysis Of Laminated Composite Plates Using Design Of Experiments Approach", International Journal of Scientific Engineering and Technology, Vol.2, Issue No.1, pp. 40-49, 2013
14. Junaid Kameran Ahmed, "Static and Dynamic Analysis of Composite Laminated Plate", International Journal of Innovative Technology and Exploring Engineering, Vol.3, Issue 6, 2013