

# Experimental Study of Replacement of Cement by Bagasse Ash with steel fibers

Mr.J.L.Batra, Assistant Prof. S.S.Kadam.

PG student SKN college of engineering korti, Pandharpur,Maharashtra,India.

Email:- [jitu.batra9@gmail.com](mailto:jitu.batra9@gmail.com)

Assistant Professor Of civil Engineering Department,SKN sinhgad college of engineering Korti,Pandharpur  
Maharashtra,India

Department of civil Engineering,SKNCOE,Korti,Pandharpur,Dist:- Solapur,

**Abstract**— Aim of the project is to utilize the waste product bagass ash produced by agricultural industry and enhancement of concrete strength by using steel fiber. Sugarcane bagasse ash (SCBA) is a left-over industrial west product which is used as a replacement of cement. Sugarcane bagasse ash has high content in silica. Using of Sugarcane bagasse ash in concrete is a remarkable possibility for economy and conservation of natural resources. One of the important properties of steel fiber reinforced concrete is its superior resistance to cracking. As a result of this ability to arrest cracks, fibers are able to hold the matrix together even after extensive cracking. In this project Sugarcane bagasse ash has been partially replaced with cement in the ratio of 0%, 5%, 10%, 15% and 20% by the weight of cement in M60 Grade concrete. From the test results optimum percentage of Sugarcane bagasse ash has achieved on steel fiber reinforced concrete.

**Keywords**— Bagasse Ash, concrete, Crimped steel fiber, partial replacement, Compressive strength, flexural strength, Split tensile strength.

## Introduction

There are many Innovations are developing world wide to control and regulate the management of sub-products, residuals and industrial wastes in order to preserve the environment from contamination. A good solution to the problem of recycling of agro industrial residue would be by burning them in a controlled environment and use the ashes (waste) for more noble means. Utilization of such wastes as cement replacement materials may reduce the cost of concrete production and also minimize the negative environmental effects with disposal of these wastes.

Sugarcane is one of the major crops grown in over 110 countries and its total production is over 1500 million tons. After the extraction of all economical sugar from sugarcane, large fibrous residue is obtained. When bagasse is burnt in the boiler of cogeneration plant under controlled conditions, reactive amorphous silica is formed due to the combustion process and is present in the residual ashes known as Sugarcane Bagasse Ash. This amorphous silica content makes bagasse ash a useful cement replacement material in concrete. Each ton of sugarcane generates approximately 20% of bagasse (at a moisture content of 50%) and 0.62% of residual ash. The residue after combustion presents a chemical composition dominates by silicon dioxide (SiO<sub>2</sub>). In this study the bagasse ash is planned to use as the partial replacement for cement in order to utilize the wastages and to protect the environment from the hazards. Sugarcane bagasse ash is normally used as fertilizer in sugarcane plantation.

Concrete is characterized by brittle failure, the nearly complete loss of loading capacity, once failure is initiated. This can be overcome by the inclusion of a small amount of short randomly distributed fibers (steel, glass, synthetic and natural). Steel fiber reinforced concrete has the ability of excellent tensile strength, flexural strength, shock resistance, fatigue resistance, ductility and crack arrest. Therefore, it has been applied abroad in various professional fields of construction, irrigation works and architecture. There are currently 300,000 metric tons of fibers used for concrete reinforcement. Steel fiber remains the most used fiber of all (50% of total tonnage used).

## NEED AND ADVANTAGES

### Need of Sugarcane Bagasse Ash (SCBA) Usage

1. Each ton of cement produces approximately about one ton of CO<sub>2</sub> and cement.
2. Brings positive effect to the environment.
3. When used as replacement for cement in concrete, it reduces the problem associated with their disposal.
4. Decrease in the emission of greenhouse gases. Construction industry is responsible for the emission of About 5% of CO<sub>2</sub> worldwide.

## Need of steel fiber

Steel fibers will enhance hardened state properties of structural concrete. Additionally, they are often used to replace or supplement structural reinforcement. Essentially, fibers act as crack arrester restricting the development of cracks and thus transforming an integrally brittle matrix, i.e. cement concrete with its low tensile and impact resistances, into a strong composite with superior crack resistance, improved ductility and distinctive post-cracking behavior prior to failure.

## Advantages

1. The ash disposal problem from sugar industry is reduced since it is usually disposed of in open land area.
2. Due to partial replacement of cement in concrete results, overall price involved in the construction is reduced.
3. Steel fibers are employed as an additive to the concrete in order to increase the energy absorption capacity and to control the crack development. It is advantageous in seismic resistant structures.

## EXPERIMENTAL INVESTIGATION

In this experimental work, a total of 96 numbers of concrete samples were casted. The typical size of cube 150mm×150mm×150mm is used. The mix design (procedure) of concrete was done according to Indian Standard guidelines for M60 grade. To achieve optimum value of SCBA on steel fiber reinforced concrete tests were divided into two parts. In first part optimum value of SCBA was founded from normal concrete. For that, concrete specimens were casted with partial replacement of sugarcane bagasse ash as 0%, 5%, 10%, 15% and 20% by the weight of cement. In second part optimum percent of steel fiber was founded from SCBA concrete. In that optimum value of SCBA replacement kept as fixed and crimped type steel fiber is added 0, 0.5%, 1% and 1.5% by the volume fraction of concrete were estimated. The ingredients of concrete were thoroughly mixed in mixer machine till uniform consistency was achieved. Before casting, machine oil was smeared on the inner surfaces of the cast iron mould. Concrete was poured into the mould and compacted carefully using table vibrator. The top surface was over by means of a trowel. The specimens were removed from the mould after 24hours and then cured under water for a period of 7 and 28 days. The samples were taken out from the curing tank just prior to the test. The compressive test was conducted using a 1000kN capacity compression testing machine. This test was lead as per the relevant Indian Standard specifications.

## MATERIAL PROPERTIES

### Cement

The cement used in this study was OPC 53 grade from Dalmia Cement Company which is widely used in the Construction industries and it conforming as per IS 12269-1987.

**Table 1: Physical properties of cement**

PROPERTY VALUE	VALUE
Specific Gravity	3.15
Standard consistency	32.5%
Setting time	-
i) Initial setting time	45 min.
(ii) Final setting time	330 min.

**Table 2: Chemical composition of cement**

COMPONENT	%
SiO <sub>2</sub>	21.8
Al <sub>2</sub> O <sub>3</sub>	4.8
Fe <sub>2</sub> O <sub>3</sub>	3.8
CaO	63.3
SO <sub>3</sub>	2.2
MgO <sub>3</sub>	0.9
Na <sub>2</sub> O	0.21
K <sub>2</sub> O	0.46
Cl	0.04
P <sub>2</sub> O <sub>5</sub>	<0.04
Loss of ignition	2
Insoluble residue	0.4

### Fine Aggregate

Aggregates for the concrete were obtained from approved suppliers conforming to the specifications of IS 383 - 1970 and were chemically inactive (inert), spotless and robust. The fine aggregate was tested as per the limits which is specified in IS: 2386 (Part- 3):1963. In this study, fine aggregate having a fineness modulus of 2.46 which is carried out by using sieve analysis and it confirming to zone 3.

**Table 3 : Physical properties of Fine aggregate**

PROPERTY	VALUE
Specific gravity	2.65
Fineness modulus	2.46
Type of sand	River sand
Sand confirming zone	Zone III (Medium sand)

### Coarse Aggregate

Coarse aggregates will be machine-crushed one of black trap or equivalent black tough stone and shall be stiff, robust, dense, durable, spotless or procured from quarries approved by the consultant. In this study, crushed aggregate of size 20 mm in angular shape is used and it conforming to IS 383-1970.

**Table 4 : Properties of Coarse Aggregate**

PROPERTY	VALUE
Specific gravity	2.67
Fineness modulus	7.682
Impact value	22.12%
Crushing value	24.44%

### Sugarcane Bagasse Ash

It comprises high volume of  $SiO_2$ . Therefore, it is classified as a good pozzolanic material. SCBA can be used as an add-on for cementitious material due to its pozzolanic property.

**Table 5 : Physical properties of Sugarcane Bagasse Ash**

PROPERTY	VALUE
Fineness modulus	2.12
Specific gravity	1.78

**Table 6 : Chemical composition of Sugarcane Bagasse Ash**

OXIDES	SCBA MASS %
Silica ( $SiO_2$ )	68
Alumina ( $Al_2O_3$ )	3.05
Ferric Oxide ( $Fe_2O_3$ )	3.72
Calcium Oxide (CaO)	5.1
Magnesium Oxide (MgO)	1.15
Sulfur Tri Oxide ( $SO_3$ )	0.67
Loss of Ignition	4.5

### Water

Good potable water available in the site is used for the construction purpose which conforming to the requirements of water for concreting and curing as per IS: 456-2009.

### Steel fiber

Steel fiber used in this study was crimped type steel fiber. Photograph of this fiber is shown in Fig.1. Properties of fiber are shown in Table 6. Fibers were placed randomly oriented into the concrete.



**Table 7 : Properties of steel fiber**

PROPERTY	VALUE
Length	30mm
Cross sectional diameter	1mm
Undulation width	2mm
Aspect ratio	50

## RESULTS AND DISCUSSION

### Compressive strength test

Compressive strength was done for the cube samples of size 150 mm x 150 mm x 150 mm. During first part of test concrete cubes were casted with partial replacement of cement with sugarcane bagasse ash as 0%, 5%, 10%, 15% and 20% and it was verified at the age of 7 and 28 days. The test results are plotted in the graph as shown in the Fig. Bellow.

Compressive strength constantly increases as the curing period goes on increasing. Maximum compressive strength achieved on 15% replacement of SCBA. In which compressive strength is 73.66 Mpa when cement replaced by bagass ash with 20% amount.

Sr.No	SCBA %	COMPRESSIVE STRENGTH IN MPa	
		7 day's	28 day's
1	0	47	67
2	5	48.33	68.33
3	10	50.11	70.11
4	15	53.22	73.66
5	20	44.33	64.77

At second of part test concrete cubes were casted with optimum value of 15% replacement SCBA kept as constant and crimped type steel fiber is added 0, 0.5%, 1% and 1.5% by the volume fraction of concrete. It was verified at the age of 7 and 28 days. The test results given bellow.

Sr.No	% of steel fiber	COMPRESSIVE STRENGTH IN MPa	
		7 day's	28 day's
1	0	49.5	68.80
2	0.5	50.66	70.33
3	1	52.44	74.50
4	1.5	51.80	70.40
5	2	46.11	66.60

From the test results maximum compressive strength was achieved on 1% addition of steel fiber. In which compressive strength is 74.50% on SCBA concrete with Steel fiber.

### Split tensile strength test

Split tensile test was done on cylinder specimens of size 150 mm in diameter and 300 mm in length. The cylinder specimen with partial replacement was done which carried out as same as the compressive strength and it is verified at the age of 28 days. The split tensile strength test results of normal concrete for different % of SCBA are shown bellow.

Sr.No	SCBA %	SPLIT TENSILE STRENGTH IN MPa	
		7 day's	28 day's
1	0	2.53	3.52
2	5	2.67	3.76
3	10	3.11	3.91
4	15	3.25	4.14
5	20	2.68	3.48

Split tensile strength of concrete goes on increasing by increase in SCBA up to the optimum value. The optimum value of SCBA content was found to be 15%. Due to SCBA replacement split tensile strength is 4.14Mps

The split tensile strength test results of SCBA concrete for different % of steel fiber are shown below.

Sr.No	% of steel fiber	SPLIT TENSILE STRENGTH IN MPa	
		7 day's	28 day's
1	0	2.68	3.82
2	0.5	2.77	3.98
3	1	3.28	4.30
4	1.5	2.92	3.92
5	2	2.1	3.28

From the test results maximum Split tensile strength was achieved on 1% addition of steel fiber is 4.30 Mpa

#### Flexural strength test

Flexural strength test was done on beam specimens of size 100 mm X 100 mm X 500 mm. The beam specimen with partial replacement was done which carried out as same as the compressive strength and it is verified at the age of 28 days. The flexural strength test results of normal concrete for different % of SCBA are shown below.

Sr.No	SCBA %	FLEXURAL STRENGTH IN MPa	
		7 day's	28 day's
1	0	4.2	6.3
2	5	4.46	7.18
3	10	4.66	7.66
4	15	4.78	8.38
5	20	3.76	6.1

It was founded that, at the age of 28 days, maximum flexural strength was obtained at 15% replacement of SCBA is 8.38Mpa.

The flexural strength test results of SCBA concrete for different % of steel fiber are shown below.

Sr.No	% of steel fiber	FLEXURAL STRENGTH IN MPa	
		7 day's	28 day's
1	0	4.50	6.60
2	0.5	4.76	7.38
3	1	4.84	8.96
4	1.5	5.1	7.53
5	2	4.1	6.4

From the test results maximum flexural strength was achieved on 1% addition of steel fiber is 8.96 Mpa.

#### ACKNOWLEDGMENT

Our sincere gratitude to family members, friends, teachers, and also acknowledge the support and help of all others who all concerned about this thesis

#### CONCLUSION

From this experiments and research work the following facts are drawn

- The compressive strength of sugar cane baggas ash concrete M60 Grade is comparatively higher than that of Normal control mix
- The compressive strength of sugar cane baggas ash concrete M60 Grade is comparatively greater which is 73.66Mpa and it also increases with addition of 1% of steel fiber, its compressive strength after addition of steel fiber is 74.50 Mpa.
- Spilt tensile strength of sugar cane baggas ash concrete M60 Grade is comparatively greater which is 4.14Mpa and it also increases with addition of 1% of steel fiber, its Spilt tensile strength after addition of steel fiber is 4.30 Mpa
- flexural strength of sugar cane baggas ash concrete M60 Grade is comparatively greater which is 8;38Mpa and it also increases with addition of 1% of steel fiber, its Spilt tensile strength after addition of steel fiber is 8.96 Mpa
- So finally we conclude that we are able to replace cement by 15 % baggas ash.

## REFERENCES:

- [1] I.S.S. Kadam and V.V. Karjinni (2017), "Effect of different aspect ratio of steel fiber on mechanical properties of high strength concrete", The Indian Concrete Journal, Vol.91, No.5 pp 60-68.
- [2] S. S. Kadam and Dr. V.V. Karjinni (2018), "Evaluating the use of high strength concrete pavement Quality course made with steel fiber and silica fume", Indian Highways, Vol.46, No. 2, pp 11-18
- [3] Falah A. Almortiri (2011) 'Physical Properties of Steel Fiber Reinforced Cement Composites Made with Fly Ash', Jordan Journal of Civil Engineering, Volume 5, No. 2, PP.278-286.
- [4] IS 456 - 2000, 'Plain and Reinforced Concrete-Code of Practice', Bureau of Indian Standards, New Delhi
- [5] IS 10262 - 2009, 'Indian Standard Concrete Mix Proportioning-Guidelines', Bureau of Indian Standards, New Delhi.
- [6] IS 516 - 1959 'Indian Standard for Methods of Test for Strength of Concrete', Bureau of Indian Standards, New Delhi.
- [7] IS 12269 - 1987, 'Specification for 53 Grade Ordinary Portland Cement', Bureau of Indian Standards, New Delhi.
- [8] IS 2386 - 1963, 'Methods of test for aggregates for concrete', Bureau of Indian Standards, New Delhi.
- [9] IS 383-1979 (Reaffirmed 1997), 'Indian Standard Specification for Coarse and Fine Aggregates from Natural Sources for Concrete', Bureau of Indian Standards, New Delhi.
- [10] Lavanya M.R, Sugumaran.B, Pradeep.T (2012) 'An Experimental study on the compressive strength of concrete by partial replacement of cement with sugarcane bagasse ash', IJEEI journal, Volume 1, Issue 11, PP: 01-04.
- [11] Milind V. Mohod (2014) 'Performance of Steel Fiber Reinforced Concrete', RESEARCH INVENTY Journal, Vol. 1, Issue 12 (December 2012), PP 01-04.
- [12] R.Srinivasan, K.Sathiya (2010) 'Experimental Study on Bagasse Ash in Concrete', International Journal for Service Learning in Engineering, Vol. 5, No.2, pp.60-66.
- [13] T. S. Abdulkadir, D. O. Oyejobi, A. A. Lawal (2014) 'Evaluation Of Sugarcane Bagasse Ash As A Replacement for Cement In Concrete Works', ACTA TEHNICA CORVINIENSIS – Bulletin of Engineering Fascicule 3 [July – September] Tome VII .
- [14] U.R.Kawade, Mr.V.R.Rathi, Miss Vaishali D. Girge (2013) 'Effect of use of Bagasse Ash on Strength of Concrete', International Journal of Innovative Research in Science, Engineering and Technology Vol. 2, Issue 7, pp. 2997-3000.
- [15] Vikrant S. Vairagade, Kavita S. Kene (2012) 'Introduction to Steel Fiber Reinforced Concrete on Engineering Performance of Concrete', IJSTR Journal, Volume 1, Issue 4, pp: 139-141.
- [16] Yashwanth.M.K, Dr.B.G.Nareshkumar (2014) 'An Experimental Study on Bagasse ash as Replacement for Cement in Lightweight Concrete', IJLTET Journal, Vol. 3, Issue 3, pp:253-260.